

## Diamonte

### Deck Pressure Washing and Staining Wood Decks Specifications

1. Pre-treat clean deck flooring per manufacturer recommendations.



- a. Removes mold and some staining.
  - b. Walls, pillars and lower areas need to be covered for protection. This means using painter tape and plastic to be sure no stain gets on the walls, pillars, deck skirt or area under the deck.
2. Pressure wash deck flooring – must have 48 hours of deck drying with no dew or rain.
  3. Spot sand deck flooring of any areas with oil or rough edges
  4. Staining deck floors – only to be completed in shade conditions and dry deck
    - a. Any of these TWP products may be used - TWP 101 Cedar Tone Natural or 301 series Cedartone or 1501 series Cedar
    - b. Two Coats wet on wet application is acceptable that means everything is cleared off the deck for two thorough coats.
    - c. Tarp lower areas to catch possible drips

